



LIBOLON N200-260

Product description LIBOLON N200-260 is a polyamide 6 grade of high viscosity that is well suited for production of monofilament. Lubricants and soft agent are added to improve transparency, clarity, softness and anti-blocking.

Supply form and storage LIBOLON N200-260 is supplied pre-dried and ready for processing in a variety of moisture proof containers, such as boxes, bigbags and bulk containers.

Quality Acceptance LIBOLON N200-260 meet the requirements of "Heavy Metal Test", "RoHS" and FDA 21 CFR 177.1500 " Nylon Resins".

Test Item		Test Methods	Unit	Actual
Physical Properties	Diameter of Chip	-	mm	2.0~2.5
	Weight of Chip	-	g/100pc	0.88-0.98
	Density	ASTM D792	g/cm ³	1.13
	Moisture Absorption	ASTM D570	%	5.29 (50% RH)
Mechanical Properties	TensileYield Strength	ASTM D638	Mpa	54.6
	Elongation at Break	ASTM D638	%	280
	Flexural Strength	ASTM D790	Mpa	42.8
	Flexural Modulus	ASTM D790	Mpa	879.8
	IZOD Notched Impact Strength	ASTM D256	J/m	79.48
	Hardness	ASTM D2240	share D	84
Thermal Properties	Temp of Deflection	ASTM D648	°C	50.9
	UL Flammability	UL94/1.6mm	-	V2
	Melting Point	DSC	°C	222
	Melting Index 270°C, 1.2kg	-	g/10min	10.71
Electrical Properties	Surface Resistance	ASTM D257	ohm	3.0×10 ¹⁴
	Volume Resistance	ASTM D257	ohm*cm	1.02×10 ¹⁵
	Dielectric Strength	ASTM D149	kV/mm	12.5
	Dielectric Constant at 1MHz	ASTM D150	kV/mm	5.29

OFFICE
6F, No.162, Sung Chiang Rd., Taipei 104,
Taiwan, R.O.C

TEL : (02) 21002188
FAX : (02) 21002178

www.libolon.com.tw

PLANT
No. 33, Gongye Rd. Fangyuan Ind. Park, Changhua
528, Taiwan, R.O.C

TEL : (04) 8953888
FAX : (04) 8953889